



IMPAX UV PC

UV PROTECTED EXTRUDED POLYCARBONATE

GENERAL			
Density	ISO1183	1.20	g/cm ³
Water Absorption	ISO62	0.2	%
MECHANICAL			
Tensile Strength	ISO527-2	60	MPa
Elongation at Break	ISO527-2	80	%
Tensile Modulus	ISO527-2	2300	MPa
Flexural Strength	ISO178	90	MPa
Flexural Modulus	ISO178	2300	MPa
Charpy Impact Strength, Notched	ISO179-1	40	kJ/m ²
Izod Impact Strength, Notched	ISO180/1A	70	kJ/m ²
THERMAL			
Vicat Softening Temperature, B50, Annealed	ISO306	135	°C
Heat Distortion Temperature, 1.8MPa	ISO75	125	°C
Linear Thermal Expansion	DIN53752	7	/°K x 10 ⁻⁵
Continuous Service Temperature	-	110	°C
Maximum Short Term Temperature	-	120	°C
Degradation Temperature	-	> 280	°C
OPTICAL			
Light Transmission Clear (3mm)	520nm	88	%
Light Transmission Grey (3mm)	520nm	50	%
Refractive Index	DIN5036-3	1.59	-

This specification provides reliable and accurate data to the best of our knowledge at the time of publishing. Due to our inability to control conditions of use and application, we are unable to make any recommendations or suggestions. The EGR Group (Oakmoore Pty Ltd) assumes no liability for use of information presented herein.